

Materials characteristic

Remag 28 I-HT

Type: Isostatically pressed

Magnetic properties:

Characteristic	Designation	Unit	Typical	Minimum
Remanence	Br	T	1.11	1.08
Coercivity	bHc	kA/m	835	800
Intrinsic Coercivity	iHc	kA/m	2700	2300
Energy product	(BH) _{max}	kJ/m ³	235	215

The magnetic properties may vary depending on shape and size of the magnet. Given values relate to dimension ratio h/D = 1.

Physical properties:

Characteristic	Unit	Value
Density	g/cm ³	8.4
Elasticity Modulus	kN/mm ²	120
Bending Strength	N/mm ²	120
Compression Strength	N/mm ²	800
Hardness	HV	600
Specific Electrical Resistance	μΩcm	85
Specific Heat	J/kgK	280
Specific Thermal Conductivity	W/mK	12
Curie Temperature	°C	800
Temperature Coefficient ; -TK _{Br}	%/°C	-0.04
Temperature Coefficient; -TK _{iHc}	%/°C	-0.20
Required Magnetisation Strength	kA/m	5000
Max. Working Temperature	°C	350

Chemical composition: (acc. DIN IEC 60404-8-1)

Element	Nominal (wt.%)
Sm	24 - 26
Co	48 - 52
Fe	13 - 18
Cu	1.5 - 12
Zr	0 - 3

